

CMX fusible

Article Description	Tear-away backing with iron-on coating
Material composition	80% wood pulp, 20% polyester
Weight	48g/m ² (CMX 35)
Colours	white & black

Characteristics

- Very stable, but still pleasantly soft
- Can be framed tightly
- Full-surface iron-on coating

Care instructions

Washing and ironing temperatures, detergents, etc. depend on the fabric being embroidered. Once the embroidery process is complete, the material is completely removed by tearing. Any residue will be removed by washing.

Always do a test run before production!

Application instructions

Place the backing on the wrong side of the fabric with the coated side down and press with heat press or iron:

Heat press: 104°C – 132°C | 4-6 seconds | 2-4 bar
Iron: medium heat (two dots; with steam) | 5 seconds

Certificates



STANDARD 100 by OEKO-TEX®, annex 4, product class I

Disposal

Offcuts can be disposed of with your household waste.

To improve this product Madeira reserves the right to alter the specifications or modify the appearance of products without notice. Information and technical data in this document are guidelines and no warranted characteristics. Small variations due to production process are possible.